





SMI

STYRENE MONOMER SPECIFICATION

PROPERTY	UNIT	SPECIFICATION		ASTM TEST METHOD
Purity	wt%	99,8	min.	ASTM D 5135
Aldhydes, as Benzaldehyde	wt%	0,0100	max.	ASTM D 2119
Peroxide as H ₂ O ₂	mg/kg	50	max.	ASTM D 2340
Polymer	mg/kg	10	max.	ASTM D 2121, test method A
Inhibitor	mg/kg	10 to 15 (or as required)	max.	ASTM D 4590
Ethylbenzene	mg/kg	500	max.	ASTM D 5135
Benzene	mg/kg	1	max.	ASTM D 6229
Water	mg/kg	if needed		ASTM D 6304 or E1064
Color	Pt/Co	10	max.	ASTM D 1209

Based on ASTM D2827-10

Rev (12) September 21, 2011

Prepared by:	Approved by:
	
QCS Manager	Factory Manager

PT Styrimdo Mono Indonesia

(Subsidiary of PT Chandra Asri)

Desa Mangunreja, Kecamatan Puloampel

Kabupaten Serang, Banten - 42456, Indonesia

T 62(254) 575 0080 F 62(254) 575 0085