



Homopolymer Polypropylene

Technical Data Sheet (TDS)

HF7.0CP

CPP Film Grade

Product Description:

Trilene® HF7.0CP is a homopolymer polypropylene resin which is supplied in natural pellet form and suitable for CPP dry lamination film requiring excellent clarity, strength and process-ability.

Product Characteristics:

- High strength
- Excellent clarity
- Good process-ability
- Low slip and antiblock additives

Applications:

- CPP dry lamination film

Physical Properties	Test Method*	Unit	Value
Melt Flow Rate (230 °C / 2.16 kg)	ASTM D 1238	g/10 min	7
Density	ASTM D 792	g/cm ³	0.9
Tensile Yield Strength (@50 mm/min)	ASTM D 638	MPa	34
Tensile Yield Elongation	ASTM D 638	%	13
Flexural Modulus (@1.3 mm/min)	ASTM D 790A	MPa	1,300
Notched Izod Impact Strength (@23 °C)	ASTM D 256	J/m	35
Hardness, Rockwell	ASTM D 785	R-Scale	100
Deflection Temperature (@0.455 MPa)	ASTM D 648	°C	104
Vicat Softening Temperature	ASTM D1525B	°C	152
Melting Temperature	ASTM D 3418	°C	163

*Polypropylene tested per ASTM D 4101

Conversion: 1 MPa = 10.2 kgf/cm²
1 kJ/m² = 0.01 kgf.cm/mm²

Recommended Processing Conditions:

Melt Temperature.....240-260 °C

Chill Roll Temperature.....25-30 °C

Product Available Form:

Natural pellet

Packaging:

25 kg woven bag

Safety:

- The product is not classified as a hazardous material.
- Please refer to our Safety Data Sheet (SDS) for details on various aspects of safety, recovery and disposal of the product.

Homopolymer Polypropylene

Technical Data Sheet (TDS)

HF7.0CP

CPP Film Grade

Storage:

- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials, food and drink, as this may lead to quality deterioration, which results in odor generation and color changes and can have negative effects on the physical properties of this product.
- Keep packaging tightly closed and sealed until ready for use. Packaging that has been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabeled packaging. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.
- Please refer to our Safety Data Sheet (SDS) for details on storage and handling of the product.

Regulatory:

- This material complies with recommendations and statutory regulations regarding packaging materials intended to come in contact with foodstuff, such as:
 - FDA Regulation 21 CFR177.1520
 - Commission Regulation EU No.10/2011
 - BPOM Regulation No.HK 03.1.23.07.11.6664 on 2011
 - Halal Certificate from The Indonesian Council of Ulama
 - SNI No.0594:2011
- Please refer to our Regulatory Data Sheet (RDS) for details on various aspects of regulatory of the product.

Product Stewardship:

PT. Chandra Asri Petrochemical, Tbk. (CAP) has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health and environmental information on our products and then take appropriate steps to protect employee, public health and environment. The success of our Product Stewardship program rests with each and every individual involved with CAP products –from the initial concept and research, to manufacture, storage, sale, use and disposal of each product.

Disclaimer:

The nominal properties reported herein are typical on the product of CAP but do not reflect normal testing variance and therefore should not to be construed as specifications.

CAP reserves the right to make any improvement or amendments to the composition of any grade or product without alteration to the product code.

This document reports accurate and reliable information to the best of our knowledge on the products manufactured by CAP. Since CAP cannot anticipate or control the conditions under which this information and its product may be used, each user should review the information in the specific context of the intended application. CAP will not be responsible for damages of any nature resulting from the use of or reliance upon the information.

This technical datasheet is effective as from **July 2016** and supersedes all data previously published.

PT. Chandra Asri Petrochemical, Tbk.

Site Office:
Jl. Raya Anyer Km. 123, Ciwandan, Cilegon,
Banten 42447, Indonesia
P: +62 254 601501, F +62 254 601505
E: GROUVRND@capcx.com

Head Office:
Wisma Barito Pacific Tower B, 2nd Floor
Jl. Let. Jend. S. Parman Kav. 62-63
Jakarta 11410, Indonesia
P: +62 21 5307950, F +62 21 5308930
www.chandra-asri.com



QMS ISO 9001
EMS ISO 14001
OHSAS 18001